# Integra Adhes ves

### **SURFACE BONDER XI**

A semi-automated mix and dispenser system composed of a dual component cartridge, static mixer and a hand-held dispenser



The system accurately measures, mixes and dispenses the correct amount of pre-colored adhesive, providing consistent results, fast and uniform cure, reliable bond strength and minimal waste.



## **INTEGRA SURFACE BONDER XI**

Surfacing adhesive for Solid Surface, Quartz, Ceramic, Natural Stone, and more...

#### **APPLICATIONS**

Fabrication of laminations and deck seams for: QUARTZ SURFACES Silestone, Caesarstone, Cambria, Okite, etc... NATURAL STONES Granite, Marble, Limestone, etc... SOLID SURFACES Corian, Staron, LG Hi-Macs, Avonite, etc... AND MORE

#### **ADVANTAGES**

Auto-dispense system Eliminates hand-mixing Invisible seams 300+ pre-mixed colors High strength UV stable Working time 12 minutes Fixture time 25 minutes Indoor Air Quality Certified LEED Certified

#### CONTACT

PHONE 1.888.862.6665 1.604.850.1321 FAX 1.604.850.1354 EMAIL & WEB contact@integra-adhesives.com www.integra-adhesives.com

Integr<u>a</u> Adhesjves

#### **Product Overview**

Surface Bonder Xi is the latest generation of color matched adhesives for the surfacing industry. Available in more than 300 pre-mixed colors; developed for modern demanding fabrication methods such as laminating, mitreing, v-grooving, integral mounted sinks and bowls, and applications subject to dynamic loads.

Surface Bonder Xi produces improved bond strength over competitor products. Fabricators benefit from increased color choices as Xi is used universally on Acrylic and Polyester Solid Surface materials as well as Granite, Marble, and Quartz Surfaces.

Integra's reputation for innovation and product development continues with the first color matched adhesive cartridge system specifically designed for the stone industry. The system includes a special coloration system, low waste mixing tips, improved cartridges, and low cost dispensers.

#### Characteristics

Appearance — Component A	Clear or colored viscous liquid
Appearance — Component B	Clear to white viscous liquid
Viscosity A	40,000 – 150,000 CPS
Viscosity B	20,000 – 25,000 CPS
Density	1.11 g/L
Working Time	10-15 minutes
Fixture Time	20-30 minutes
Recommended Bond Line	0.002 – 0.040 inches (0.5 – 1.0mm)
Bond Strength (Solid Surface) — Flexural	4000 – 6000 PSI (280 – 420 kg/cm²)
Bond Strength (Quartz) — Flexural	3000 – 4000 PSI (210 – 281 kg/cm²)
Shelf Life — Component A	1–2 years
Shelf Life — Component B	1 year
Mix Ratio A/B (Volume)	10/1 optimum

#### **Color Matching**

Integra is known industry wide for its excellence in matching colors. The lab uses a combination of technical equipment and experience to produce unrivalled color matches for every surface. Color match charts are updated regularly with new matches for new sheets from manufacturers. While most surfaces can be matched using the top 20-30 adhesive colors, Integra customers have access to a pallette of over 300 colours, and our lab can produce any colour under the sun should the need arise.

#### **Dispensing / Packaging**

Surface Bonder Xi is packaged in dual component cartridges as part of a meter/ mix/dispense system utilising specialised dispensing guns and static mixing tips. Surface Bonder Xi is available in 100ml, 250ml and 500ml cartridges.

#### **Shipping Options**

Integra's adhesives are stocked at multiple locations across North America and Europe. A 1–2 day lead time can generally be expected for ground delivery within the continental US and Canada.